



STICKCON FIX - JOINTING MORTAR

Stiickcon Fix - Jointing Mortar is a thin jointing mortar for AAC blocks masonry work. It is manufactured to provide high strength & durable bonding between the blocks.

AREAS OF APPLICATION

Stiickcon Jointing Mortar is recommended to be used for masonry wall preparation for joining all types of auto claved aerated concrete blocks and fly ash bricks.

FEATURES & BENEFITS

- Economical & conventional mortar
- High adhesion strength at joints
- No shrinkage cracks at joints
- Self-curing
- Thin layer joints
- Ready for subsequent application in 24 hours

TECHNICAL DATA AS PER RELEVANT IS AND ASTM STANDARDS

Bulk Density	1400-1550Kg/m
Water Powder Ratio	25% by weight
Pot Life	1 hour@27°C
Usable time post application	24 hours
Tensile Adhesion Strength @ 28 Days - EN 1348	0.8 N/mm
Splitting tensile strength @ 28 Days - AST MC 1660-09	0.75 N/mm ²
Compressive strength @ 28 Days	6-7 N/mm ²

REFERENCE

ASTM C 1660-09

COVERAGE/ 40KG BAG

3 - 5 Sq.ft. for block thickness of 100mm




Shelf Life:

Shelf life of 6 months from the date of manufacturing.


AREAS OF APPLICATION

STICKCON Jointing Mortar - is a high quality Polymer & Grey cement base, Best quality AAC Block Jointing Mortar. Self-curing & Good strength mortar for fixing AAC Blocks.

FOLLOW THE STEPS FOR APPLIATION



Clean the surface before use to remove Oil & Dust particles.



Mix Stickcon 40 kg mortar with 8 to 10 L Water..



Mix thoroughly using stirrer for 3-4 minutes & wait for 5 minutes.



Apply mortar & comb with notched trowel. For best results, maintain 3 to 6 mm thickness of material.



Wet AAC Block before use of mortar.



Recommend to use PPE during application of mortar.



CORPORATE OFFICE:

C-201, Swagat Rainforest-3, Kh Road, Sargasan, Gandhinagar-382 421. (Gujarat) INDIA

 Visit us : www.stickcon.com

Customer Care :  : +91 99090 90275  : info@stickcon.com

MANUFACTURING UNIT:

Plot No.: 262/2, Khakhariyavan Road, Villag. : Chikhalod, Ta.: Kapadeanj,

Dist. : Kheda, 387 640. (Gujarat) INDIA